



RAMOLENE™ RESIN

COPO 35

Copolymer Polypropylene

TECHNICAL DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index @ 230°C 2.16kg	35	D-1238
Density	0.9 g/cm ³	D-792
Izod Impact Strength Notched @ 23 C	2.0 (ft-lb/in)	D-256
Tensile Strength @ yield (kpsi)	3800	D-638
Flexural Modulus, 1% Secant (.05 in/min, 1.3 mm/min)	198000 (kpsi)	D-790A

All tests were run under laboratory conditions, ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Ramtech's products must be guided by the user's own methods for selection of proper formulation. RAMTECH OVERSEAS, INC. disclaims any responsibility for misuse or misapplication of its products. Ramtech makes no warranty of merchantability and there is no warranty that goods supplied shall be fit for any particular purpose.