



RAMOLENE™ RESIN

LDF 0.25 B (Film - Heavy, Shrink, Blend)

Low Density Polyethylene

TECHNICAL DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index	.25	D-1238
Density	0.920	D-792
Dart Drop Impact F50	140 grams	D-1709
Tensile Strength	MD 4200 PSI TD 2900 PSI	D-882
Elongation	MD 105% TD 400%	D-882
1% Secant Modulus	MD 27000 PSI TD 32000 PSI	D-882
Haze	30%	D-1003

Additives: Medium Antiblock (3000 PPM)

All tests were run under laboratory conditions, ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Ramtech's products must be guided by the user's own methods for selection of proper formulation. RAMTECH OVERSEAS, INC. disclaims any responsibility for misuse or misapplication of its products. Ramtech makes no warranty of merchantability and there is no warranty that goods supplied shall be fit for any particular purpose.