



# RAMOLENE™ RESIN

**LDF 2.0** (Film Clarity)

Low Density Polyethylene

# TECHNICAL DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index	2.0	D-1238
Density	0.921 g/cm <sup>3</sup>	D-1505
Haze	6.5-8.8%	D-1003
Dart Drop Impact F50	55-100g	D-1709
Tensile Strength at Yield	MD 1500-3400 PSI TD 1450-1700 PSI	D-882
1% Secant Modulus at Yield	MD 27000-31000 PSI TD 31900-35000 PSI	D-882
Elongation at Break	MD 250% TD 500-750%	D-882

Additives: No Slip, No Antiblock

All tests were run under laboratory conditions, ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Ramtech's products must be guided by the user's own methods for selection of proper formulation. RAMTECH OVERSEAS, INC. disclaims any responsibility for misuse or misapplication of its products. Ramtech makes no warranty of merchantability and there is no warranty that goods supplied shall be fit for any particular purpose.