



RAMOLENE™ RESIN

PVC K-57

Polyvinyl Chloride Homopolymer (PVC)

TYPICAL APPLICATIONS:

Ramolene™ PVC K-57 resin is well suited for a broad range of applications. Typical applications include pipe fittings and other injection molded products, calendered film and sheet, extruded sheet, bottles and plasticized applications.

Ramolene™ PVC K-57 is a low molecular weight resin designed for rigid injection molding, calendaring, sheet extrusion and blow molding.

Appearance: free flowing white powder.

TECHNICAL DATA SHEET

PROPERTY	VALUE	ASTM
K-Value	57	
Relative Viscosity	1.90	
Inherent Viscosity	0.73	D-5225
Bulk Density	0.53 (g/cc)	D-1895
Volatiles	0.20%	
Particle Size	% thru 40 Mesh 99.9 % thru 200 Mesh 7.0	D-1921
ASTM Cell Classification	GP2-16050	D-1755

All tests were run under laboratory conditions, ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Ramtech's products must be guided by the user's own methods for selection of proper formulation. RAMTECH OVERSEAS, INC. disclaims any responsibility for misuse or misapplication of its products. Ramtech makes no warranty of merchantability and there is no warranty that goods supplied shall be fit for any particular purpose.